

CLAIM AMENDMENTS

1. (original) A method for smoothly shaping a solid surface by using a gas cluster ion beam, comprising:

a process of irradiating said gas cluster ion beam by making the angle formed by said solid surface and said gas cluster ion beam less than 30° for at least a portion of the time period of said gas cluster ion beam irradiation process.

2. (original) A smoothing method according to Claim 1, wherein said gas cluster ion beam irradiation process comprises a process, preceding said process of irradiation at an irradiation angle of less than 30° , of irradiating said gas cluster ion beam on said solid surface by making the angle formed by said solid surface and said gas cluster ion beam equal to or greater than 30° .

3. (previously presented) A smoothing method according to Claim 1, comprising a process of repeating one or more times a continuous change between an irradiation angle equal to or greater than 30° and said irradiation angle of less than 30° .

4. (original) A smoothing method according to Claim 1, wherein said process of irradiation at an irradiation angle of less than 30° comprises a process of irradiation in a first direction in the plane of projection of said gas cluster ion beam on said solid surface, and a process of irradiation in a second direction, different from said first direction, in said plane of projection.

5. (original) A smoothing method according to Claim 4, wherein said process of irradiation at an irradiation angle of less than 30° comprises a process of irradiation wherein the direction in said plane of projection is continuously varied between said first direction and said second direction.

6. (previously presented) A smoothing method according to Claim 4, wherein said process of irradiation at an irradiation angle of less than 30° , in which said first and second directions mutually form an angle equal to or greater than 5° .

7. (original) A smoothing method according to any of Claims 1 to 6, wherein said solid surface is a side wall surface of a concave portion or a convex portion formed in a sample surface.

8. (original) A smoothing method according to any of Claims 4, 5, and 6, wherein the irradiation angle formed between said gas cluster ion beam and said solid surface is made to be fixed for said process of irradiation at an irradiation angle of less than 30° .

Claims 9 to 13. (canceled)